



100% solids polyurethane waterproofing membrane

DESCRIPTION

One component solventless waterproofing coating. Upon polymerization, forms an elastomeric seamless polyurethane coating, fully bonded to the substrate. Material not classified as hazardous for transportation-Non flammable.

APPLICATION

It can be applied on different substrates using a suitable primer (concrete, fibrous cement, brick, ceramic tiles, bituminous products, steel, zinc, aluminium surfaces)

- Roofs, balconies, terraces
- Bathrooms, kitchens.
- Stairs, stands.

PROPERTIES

- Crack bridging ability.
- Elastic membrane.

CERTIFICATION

CE marking EN 1504-2: 0370-CPR-2247,
Fire certification B0-roof T4



TECHNICAL DATA

INFORMATION ON THE PRODUCT BEFORE APPLICATION

Chemical description	Polyisocyanate prepolymer		
Physical state	Liquid		
Packaging	Metal container		
	25 kg		
	6kg		
	1kg		
Non-volatile content (%)	100%		
Flash point	>100°C		
Density	1.3 g/cm ³ (20°C)		
Viscosity approximate Brookfield	Temp (°C)	Viscosity (MPa)	
	(Heater belts for temperatures below 10°C are recommended)	33	5100
		25	8100
		10	22000
	4	25000	
Colour	Red. Other colours available on request		
Pot life	2h		
Storage	Keep between 10° y 30°C (recommended).		
Use before	6 months if kept in its sealed container		

INFORMATION ON THE FINAL PRODUCT

Final state	Solid elastomeric membrane	
Colour	Standard colour is Red. Other colours available under request.	
Hardness (shore)	63A (ISO 868)	
Mechanical properties	Elongation(EN-ISO 527-3): 375 %	
	Tensile strength(EN-ISO 527-3): 1.8 MPa	
Adhesion strength	Surface	Adhesion (MPa)
	Fibrous cement (EP primer)	>1,5

UV resistance	Good resistance to UV-induced degradation. Aromatic polyurethanes undergo change of colour under sunlight. This change does not affect its mechanical properties.
---------------	---

SUPPORT REQUIREMENTS

In order to achieve a good penetration and bonding, support must be:

1. Flat and levelled
2. Compact and cohesive (pull off test must show a minimum resistance of 1,5 N/mm²).
3. Even and regular surface
4. Free from cracks and fissures. If any, they must be previously repaired.
5. Clean and dry, free of dust, loose particles, oils, organic residues or laitance

RECOMMENDED ENVIRONMENTAL CONDITIONS

Substrate temperature should be between 0°C and 30°C. If higher than 45°C will reduce working time and cause bubbling and surface defects.

Air temperature should be between 10°C and 30°C. Higher temperatures reduce working time and cause bubbles and surface defects.

High humidity can cause an important decrease of working time and bubble formation under the coating surface. With temperatures lower than 10°C, heater belts are recommended.

SUPPORT PREPARATION

It is required to treat the critical spots by application of a reinforcement (e.g fiberglass, geotextile)

MIXING

Stir and homogenise gently to prevent air pick-up. Wait a few minutes before application.

APPLICATION GUIDELINES

Apply with roller, spreader. If two coats are applied, it is advisable to use different colours. Usually, each coat is 1 kg/m².

It is recommended to consume entirely each container. If not, the residues may harden superficially.

CURING TIME

Curing time for mixtures 1 mm thick, approximate:

Conditions	Dry to touch
23°C, 23% rh	1 h

TOOL CLEANING

Use Rayston solvent for general cleaning.

SAFETY

Always follow the safety instructions in the Material Safety Data Sheet. As a general rule, a good ventilation is needed) along with protective clothing. This product must be used only for the applications here described. This product is intended for industrial and professional use. It is not suitable for DIY-type applications.

ENVIRONMENTAL PRECAUTIONS

Empty containers must be handled with the same precautions as if they were full. Treat empty containers as hazardous waste, and transfer them to an authorized waste manager. If the containers still have some material left, do not mix with other product with no knowledge of potential dangerous reactions.



KRYPTON CHEMICAL SL

C/ Martí i Franquès, 12 - Pol. Ind. les Tàpies
43890 - l'Hospitalet de l'Infant - Spain
Tel: +34 977 822 245 - Fax: +34 977 823 977
www.kryptonchemical.com - rayston@kryptonchemical.com

ISO 9001

BUREAU VERITAS
Certification

N° ES110809-1



Latest update:

25/8/2020

Page:

1/2

IMPERMAX SF

RAYSTON
products



100% solids polyurethane waterproofing membrane

OTHER INFORMATION

The information contained in this DATA SHEET, as well as our advice, both written as verbal or provided through testing, are based on our experience, and they do not constitute any product guarantee for the installer, who must consider them as simple information.

We recommend to study deeply all information provided before proceeding to the use or application of any of our products, and strongly advise to conduct tests "on-site" in order to determine their convenience for a specific project.

Our recommendations do not exempt of the obligation of installers to deeply study the right application method for these systems before use, as well as to conduct as many preliminary tests as possible should any doubt arise. The application, use and processing of our products are beyond our control, and therefore under the exclusive responsibility of the installer. In consequence, the installer will be the only responsible of any damage derived from the partial or total in-observation of our indications, and in general, of the inappropriate use or application of these materials.

This data sheet supersedes previous versions.



KRYPTON CHEMICAL SL

C/ Martí i Franquès, 12 - Pol. Ind. les Tàpies
43890 - l'Hospitalet de l'Infant - Spain
Tel: +34 977 822 245 - Fax: +34 977 823 977

www.kryptonchemical.com – rayston@kryptonchemical.com

ISO 9001

BUREAU VERITAS
Certification



N° ES110809-1

Latest update:

25/8/2020

Page:

2/2