



Aliphatic one-component polyurethane resin

DESCRIPTION

Top coat of one component aliphatic polyurethane, that cures upon reaction with atmospheric moisture, giving hard and flexible coatings with good abrasion, scratch and weather resistance. High resistance chemical agents.

Excellent surface protection for use over aromatic polyurethane waterproofing membranes as UV protection.

APPLICATION

- Protecting topcoat of steel surface in anticorrosion systems
- For structures in medium, high, very high atmospheric corrosivity categories (C3,C4 Y C5- ISO 12944-2:2018)
- Protective UV topcoat for cold or hot-applied waterproofing membranes (pigmented version).
- Protection of outdoor wood surfaces
- General outdoor use

ADVANTAGES

- semigloss topcoat.
- One-component product. Easy to apply.
- Excellent resistance to atmospheric influence and abrasion
- Excellent resistance to UV and colour stability.
- Long term protection in case of use in Rayston systems.
- Fast curing

CERTIFICATIONS

- **Appius independent laboratory:** Mechanical properties, artificial weathering, watertightness and water permeability. Certificate: N° 08/32307407, Abrasion: 08/32309984, 10/101.589-1432, Slip: 10/1709-1862.
- **CE Marking :** EN 13813 SR-B2, 0-ARO0,5-IR14,7. DoP 20-210
- **ETE 16/0148 :** as protective topcoat of waterproofing membranes
- **Sunlight reflectivity certification** (white colour)
SRI index (Tecnalia Lab)
- **Antiskid certification** (DIN 51130)
Giordano Bruno Laboratory

TECHNICAL DATA

INFORMATION ON THE PRODUCT BEFORE APPLICATION

Chemical description	Solvent borne single-component aliphatic polyurethane		
Physical state	Liquid		
Packaging	Metal container: 5 ltrs /20 ltrs		
Non-volatile content (%)	>70% (pigmented)		
Flash point	36° C (ASTM D 93)		
Available colours	Colourless. Pigmented in white and gray. Other colours under request		
Density	Pigmented 1.35 g/cm3 (20°C)		
Viscosity Brookfield, approx.	Temperature (°C)	Viscosity (mPa.s)	
		Colourless	Pigmented
	5	890	1000
	10	660	800
	20	410	600
	30	230	300

VOC (g/L i %)
Voc class

VOC content: 380 g/l (pigmented) **Product subclass: i II**
Solvent based single-component performance products
Limit from 01/01/2010: 500 g/l

Pot life

Pigmented: 2 hours (forms skin on surface)

Storage

Keep at a temperature below 35°C, away from ignition sources and moisture
6 months (pigmented) after manufacture in its sealed original container.

INFORMATION ON THE FINAL PRODUCT

Final appearance	Solid elastomeric membrane	
Colour	White and gray pigmented. Other colours under request	
Hardness (Shore)	60D (pigmented)	
Mechanical properties	Pigmented Maximum elongation: 70% Tensile strength: 15 MPa	
Water vapour permeability	2.7 g/m2 Day, (UNE EN ISO 7783)	
Abrasion resistance	11 mg (taber, CS-10,1 kg)	
UV Resistance	UV resistant. Aliphatic polyurethanes are colour-stable, non-yellowing	
Slip Resistance	With quartz sand spreaded onto (0,4-0,9 mm) at 1 kg/m3: class 3 as per UNE EN 12633-2003	
Thermal resistance/use temperature	Stable up to 80°C	
SRI Index (ASTM E1980-01)	104,5-105,4 (white pigmented)	
Chemical resistance	Permanent contact (0=worst, 5=best)	
	Chemical	Conditions
	Water	15d, 80°C
	Salt water (saturated)	5d, 80°C
	Hydrochloric acid (200 g/l)	7d, 80°C
	Hydrochloric acid (20 g/l)	7d, 80°C
	Sodium hydroxide (40 g/l)	28d, 80°C
	Sodium hydroxide (4 g/l)	28d, 80°C
	Ammonia	28d, 80°C
	Bleach, pure	28d, 80°C
	Bleach (10% solution)	28d, 80°C
	Xylene	7d, 80°C
	Isopropyl alcohol	7d, 80°C
	Engine oil	28d, 80°C
	Results	
	5	
	5	
	0	
	3(dicolouration)	
	4	
	5	
	5	
	3	
	4	
	0	
	0	
	5	
Chemical resistance (superficial contact)	Conditions	Results
Acetic acid (6%)	24h	5
Hydrochloric acid (200 g/l)	7d, 80°C	0



KRYPTON CHEMICAL SL

C/ Martí i Franquès, 12 - Pol. Ind. les Tàpies
43890 - l'Hospitalet de l'Infant - Spain
Tel: +34 977 822 245

www.kryptonchemical.com - rayston@kryptonchemical.com



Aliphatic one-component polyurethane resin

Hydrochloric acid (20 g/l)	7d, 80°C	3(discolouration)
Sodium hydroxide (40 g/l)	28d, 80°C	4

SURFACE PREPARATION

Surface Type	Minimum	Recommended
Surface Profile	Ry5 (30–75 µm) (ISO 8503-1)	Ry5 (30–75 µm) (ISO 8503-1)
Steel surface	Sa 2 (ISO 8501-1)	Sa 2½ (ISO 8501-1)
Primed and previously painted surfaces	P St3; P Ma ISO 8501-2, ISO 12944-4	P Sa2; P Ma ISO 8501-2½, ISO 12944-4
Concrete	SSPC-SP 13/ NACE No. 6	SSPC-SP 13/ NACE No. 6

RECOMMENDED ENVIRONMENTAL CONDITIONS

Steel temperature should be between 10°C and 40°C. At higher temperatures, specific precautionary measures must be taken. Please follow manufacturer advice. Relative Humidity below 85%, and dew point at least 3°C lower than steel temperature.

Concrete: Support moisture should be less than 4%.

THICKNESS AND THEORETICAL SPREADING RATE

	Minimum	Maximum
Dry Film Thickness	60µ	150µ
Wet Film Thickness	86µ	215µ
Spreading Rate:	11.6 m ² /l	4.66 m ² /l

Note: Practical coverage depends on the application conditions, type of structure to be painted, roughness of the surface and application method.

MIXING

If necessary, dilute with up to 10% Solvent Rayston for viscosity adjustment.

APPLICATION

Apply by airless spraying equipment. It is not recommended the application by roller with low thickness film.

For airless spraying equipment, viscosity is likely to need adjustment. Excess pressure, along with high temperature and humidity, may give rise to micro bubbles that makes the surface to look hazy.

For pigmented applications, mix the pigment paste with Colodur by means of a low speed stirrer and wait some minutes to allow bubbles to disappear. Apply the pigmented colour normally. It is recommended to use all the pigmented mixture.

CURING TIME

Curing time is dependent on the environmental conditions. Curing rate increases with temperature and humidity rises. The following table gives a rough estimation of the curing time under diverse conditions for a 100 µ coat.

Conditions	Touch dry (h)
30°C, 50% hr	2
25°C, 50% hr	3

REAPPLICATION

A second coat can be applied when the first one is no longer sticky. Do not wait more than 24 hours for the next coat application to ensure good intercoat adhesion

RETURN TO SERVICE

Total curing depending on final use, it is recommended to wait 7-10 days. Final hardness development may take up to 15 days.

TOOL CLEANING

Cleaning with Rayston Solvent, acetone and alcohols. Once hardened, it cannot be dissolved.

FAQS

Problem	Question	Cause	Solution
Does not cure	Suitable solvent?	Some thinning solvents are not suitable	Apply a second coat using only Rayston Solvent as a diluant
Bubbles	Airless	High pressure	Lower pressure or apply thinner coats. Ambient conditions may be adverse for this application method.
Not enough opacity	Horizontal?	Not enough pigment	Mix well
	Curing rate can be slower?		Use of slow solvent Rayston can be useful

SAFETY

Contains isocyanates and flammable solvents. Always follow the instructions provided in the material safety data sheet and take the precaution described there. As a general rule, suitable ventilation must be ensured and all ignition sources must be avoided. This product is intended to be used only for the uses and in the way here described. This product is to be used only by industrial or professional users. It is not suitable for DIY-type uses.

ENVIRONMENTAL PRECAUTIONS

Empty containers must be handled taking the same precautions as if they were full. Containers must be considered as hazardous waste, to be transferred to an authorized waste manager. If there is some residual product in the containers, do not mix it with other substances without checking for possible dangerous reactions.

OTHER INFORMATION

The information contained in this DATA SHEET, as well as our advice, both written as verbal or provided through testing, are based on our experience, and they do not constitute any product guarantee for the installer, who must consider them as simple information.

We recommend to study deeply all information provided before proceeding to the use or application of any of our products, and strongly advise to conduct tests "on-site" in order to determine their convenience for a specific project.

Our recommendations do not exempt of the obligation of installers to deeply study the right application method for these systems before use, as well as to conduct as many preliminary tests as possible should any doubt arise. The application, use and processing of our products are beyond our control, and therefore under the exclusive responsibility of the installer. In consequence, the installer will be the only responsible of any damage derived from the partial or total in-observation of our indications, and in general, of the inappropriate use or application of these materials.

This Data Sheet supersedes previous versions.

